

# EPIC


## Photopolymer Plates

### The Industry Standard For Capped Plates

MacDermid EPIC\* photopolymer plates are the plates printers rely on most to meet their high-resolution process color printing demands.

Our EPIC plates offer a proprietary print surface and carefully balanced physical properties to provide excellent graphic reproduction, while offering better wear resistance. MacDermid EPIC plates' unique, micro-rough surface texture provides excellent ink transfer for smooth and bold solids, and because they offer the widest exposure latitude of any photopolymer plates available, you no longer need to guess the proper exposure time for line copy printing, process color or combinations of both.

For the most user-friendly printing plate in the industry, count on the company that says "Yes WE Can," MacDermid.



### Key Features

- Exceptional exposure latitude requiring no masking
- Excellent ink transfer ensuring smoother solids with no pinholes
- Improved wear resistance for longer runs
- Clean printing with fewer stops for plate clean up
- Fast and accurate mounting

### Segments

Flexible Packaging



Folding Carton



Tags & Labels



Sacks, Paper, Multiwall



**YES WE CAN**<sup>SM</sup>

**MacDermid**  
Printing Solutions

# EPIC

## Photopolymer Plates

### Technical Specifications

EPIC \* is available in thicknesses of 0.030" - 0.112" and in sizes up to 52" x 80". Please contact your JV Imaging Solutions Account Manager for details

EPIC has a hardness of 50 Shore A.

### Reproduction capabilities

**Halftones:** 1-98% at 150 lpi (60 lines/cm)

**Fine lines:** 0.003 in. (0.076mm) width

**Isolated dots:** 0.005 in. (0.127 mm) diameter

### Plate processing

Most safe-solvent solutions may be used.

Processing times for any particular job are determined by equipment, copy requirements and plate thickness.

<u>Recommended times</u>	<u>.045"</u>	<u>.067"</u>	<u>.107"</u>
Back exposure (sec.)	80-90	20-30	80-100
Face exposure (min.)	7-35	7-35	7-35
Washout (min.)	5.0	5.0	8.3
Drydown (min.)	90	90	90
Post exposure (min.)	10	10	10
Detack (min.)	10	10	10

### Ink/Solvent Compatibility

EPIC photopolymer is compatible with UV, alcohol, water, and glycol based inks. EPIC is not recommended for use with oil-based inks or hydrocarbon solvents.

### Applications

EPIC is recommended for high quality printing on film and preprint liner, particularly for process color. EPIC can also be used successfully in other applications such as high quality labels and folding cartons.

## YES WE CAN<sup>SM</sup>

It takes more than innovative, high performance products and superior technical service to help our customers compete and win in today's global marketplace. It takes a total commitment to understand their needs and the ability to provide the right solutions - every time.

When success is your only goal, trust the company that says "Yes We Can."

© 2009MacDemid, Inc.All rights reserved.

## Distributed by:



For more information, please contact us at:

1257 f Kennestone Circle, Marietta, GA 30066

p 770.420.4006 \* 800.464.2931 \* f 770.420.2952

www.jvisinc.com

